



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>5</sup> : C07D 319/06, C08F 120/18, C08G 65/32, 63/19		A1	(11) International Publication Number: WO 94/17057
			(43) International Publication Date: 4 August 1994 (04.08.94)
(21) International Application Number: PCT/SE93/00360 (22) International Filing Date: 26 April 1993 (26.04.93) (30) Priority Data: 9300145-1                  20 January 1993 (20.01.93)          SE (71) Applicant (for all designated States except US): PERSTORP AB [SE/SE]; S-284 80 Perstorp (SE). (72) Inventor; and (75) Inventor/Applicant (for US only): SÖRENSEN, Kent [SE/SE]; Rönnvägen 4, S-284 35 Perstorp (SE). (74) Agent: STENBERG, Yngve; Perstorp AB, S-284 80 Perstorp (SE).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  Published With international search report.	
(54) Title: CYCLOALIPHATIC ACRYLIC MONOMER			
<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;"> <p>(I)</p> </div> <div style="text-align: center;"> <math display="block">\text{O}-(\text{R}_3)_n-\overset{\text{O}}{\parallel}{\text{C}}-\underset{\text{R}_4}{\text{C}}=\text{CH}_2</math> <p>(a)</p> <math display="block">\text{O}-(\text{R}_3)_n-\overset{\text{O}}{\parallel}{\text{C}}-\underset{\text{R}_4}{\text{C}}=\text{CH}_2</math> <p>(b)</p> </div> </div>			
(57) Abstract			
<p>Cycloaliphatic acrylic monomer having general formula (I) in which formula R<sub>1</sub> is H, CH<sub>3</sub>, HO, HO-(R<sub>3</sub>)<sub>n</sub> or (a) and R<sub>2</sub> is (b) wherein R<sub>3</sub> is C<sub>2</sub>H<sub>5</sub>O, C<sub>3</sub>H<sub>7</sub>O, C<sub>4</sub>H<sub>9</sub>O, C<sub>6</sub>H<sub>5</sub>O or combinations thereof, R<sub>4</sub> is H or CH<sub>3</sub> and wherein the mean value <math>\bar{n}</math> for n is 1-24. The acrylic monomer is based on ethoxylated, propoxylated, butoxylated and/or phenylethoxylated 1,3-dioxane alcohols and constitutes 0.1-80 % by weight, preferably 5-40 % by weight, of a radiation curing composition.</p>			

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

CYCLOALIPHATIC ACRYLIC MONOMER

The present invention relates to a cycloaliphatic acrylic monomer based on ethoxylated, propoxylated, butoxylated and/or phenylethoxylated 1,3-dioxane alcohols, which acrylic monomer primarily is intended as a component in radiation curing compositions.

Radiation curing compositions are well-known technologies and used in for instance printing inks, paints and lacquers for furniture and packaging materials as well as for adhesives, but can also comprise application areas such as dental materials. Radiation curing compositions are environmentally suitable and pleasing as they do not contain volatile solvents. They exhibit furthermore a rapid curing and through hardening when exposed to for instance ultra-violet (UV) light or electron-beams (EB). The compositions most often contain one or more oligomers having an unsaturation, normally as acrylate. These oligomers are usually high viscous and are, to obtain applicable viscosities, diluted with various monomers. The monomers are most often acrylic monomers, which monomers are esters of alcohols and acrylic or methacrylic acid. The most commonly used acrylic monomers normally have an acrylate functionality within the range of 1-4.

In radiation curing compositions used acrylic monomers include:

- Monofunctional: 2-Ethylhexyl acrylate  
2-(2-ethoxyethoxy)ethyl acrylate  
Isobornyl acrylate  
Octyldecyl acrylate
- Difunctional: Tripropylene glycol diacrylate  
1,6-hexanediol diacrylate  
Neopentyl glycol diacrylate

- Neopentyl glycol ethoxylate diacrylate
- Trifunctional: Pentaerythritol triacrylate
- Trimethylolpropane triacrylate
- Trimethylolpropane ethoxylate triacrylate
- Glycerol propoxylate triacrylate
- Tetrafunctional: Pentaerythritol ethoxylate tetracrylate
- Di-trimethylolpropane tetracrylate

Some of the above listed acrylic monomers are not included in the list of monomers issued by the Society of British Ink Manufacturers Ltd., which list voluntarily exclude monomers that due to for instance a high irritation index or toxicity not are acceptable for use in radiation curing coatings for the printing industry.

High viscous acrylic monomers having an acrylate functionality of 5 and even higher, such as dipentaerythritol pentacrylate, are also used for specific purposes.

Besides the above exemplified acrylic monomers are the cycloaliphatic 5-ethyl-1,3-dioxane-5-methanol monoacrylate and acrylates of allyl alcohols, such as trimethylolpropane allyl ethers, known.

Acrylic monomers are generally highly reactive and as such potentially hazardous being skin and eye irritants and possible sensitizers. The properties in relation to the acrylate functionality can be summarised:


- the lower the acrylate functionality is, the better are the dilution properties and the higher are the skin irritation, toxicity, volatility and odour.
- the higher the acrylate functionality is, the poorer are the dilution properties and the flexibility and the higher are the reactivity, hardness and resistance.

Low functional, i.e. mono and difunctional, acrylic monomers must, besides the excellent dilution properties, exhibit low skin irritation and low or no odour to comply with industrial hygienic demands. Above properties must, if the monomers are to be utilised properly, be combined with for instance good reactivity, final hardness and resistance. Presently available mono and difunctional acrylic monomers are most often either skin/eye irritating, highly toxic and/or highly volatile or exhibit poor film forming properties such as poor hardness and/or poor resistance. Thus, the skin irritation value for the above disclosed monomer 5-ethyl-1,3-dioxane-5-methanol monoacrylate has from evaluations performed according to OECD Guideline for Testing of Chemicals no. 404, "Acute Dermal Irritation/Corrosion" of 12 May 1983, been determined to be 2.6/2.8 (erythema/oedema). These values prove, according to "Directive of the Commission 83/467/EEC" of 29 July 1983, as published in "Official Journal of the European Communities" L 257, 1983, that the monomer is to be classified as skin irritant. It can furthermore be noted that neopentyl glycol diacrylate is suspected of being carcinogenic.

The composition and technology of radiation curing systems and acrylic monomers are further disclosed i.a. in "Chemistry & Technology of UV and EB Formulations for Coatings, Inks and Paints" - Volume 2: "Prepolymers and Reactive Diluents for UV and EB Curable Formulations" by N.S. Allen, M.S. Johnson, P.K.T. Oldring and S. Salim. © 1991 Selective Industrial Training Associates Ltd. London, U.K.

According to the present invention above disadvantages using mono and difunctional acrylic monomers have been overcome and excellent dilution properties have been combined with low skin irritation, low volatility, low viscosity, good film forming and mechanical properties and good adhesion.

The cycloaliphatic acrylic monomer according to the invention is based on ethoxylated, propoxylated, butoxylated and/or phenylethoxylated 1,3-dioxane alcohols, such as 5-methyl-1,3-dioxane-5-methanol, 5-ethyl-1,3-dioxane-5-methanol and 1,3-dioxane-5,5-dimethanol and is characterised in the general formula



in which formula

$R_1$  is H,  $CH_3$ , HO,  $HO-(R_3)_n$  or  $O-(R_3)_n-\overset{\overset{O}{\parallel}}{C}-\underset{\underset{R_4}{|}}{C}=CH_2$  and

$R_2$  is  $O-(R_3)_n-\overset{\overset{O}{\parallel}}{C}-\underset{\underset{R_4}{|}}{C}=CH_2$  wherein

$R_3$  is  $C_2H_4O$ ,  $C_3H_6O$ ,  $C_4H_8O$ ,  $C_8H_8O$  or combinations thereof,

$R_4$  is H or  $CH_3$  and wherein the mean value  $\bar{n}$  for  $n$  is 1-24.

It is, besides above disclosed 1,3-dioxane alcohols possible to use derivatives thereof, wherein one or more carbon atoms are alkyl substituted, such as 4-methyl-1,3-dioxane-5,5-dimethanol.

The cycloaliphatic acrylic monomer according to the invention is prepared in at least two steps. Initially the 1,3-dioxane alcohol is ethoxylated, propoxylated, butoxylated and/or phenylethoxylated, which means that ethylene oxide ( $R_3 = C_2H_4O$ ), propylene oxide ( $R_3 = C_3H_6O$ ), butylene oxide ( $R_3 =$

$C_4H_8O$ ) and/or phenylethylene oxide ( $R_3 = C_8H_8O$ ) is reacted with the alcohol. A combination such as ethoxylated propoxylate of the 1,3-dioxane alcohol involves two steps. The first step, in such an embodiment, is propoxylation of the alcohol and the second step ethoxylation of the propoxylated alcohol. The resulting product from the ethoxylation, propoxylation, butoxylation and/or phenylethoxylation is finally esterified with acrylic and/or methacrylic acid to obtain the acrylic monomer. Instead of a direct esterification with above acrylic acids can a transesterification using acrylates such as ethylacrylate, butylacrylate etc. or corresponding methacrylates, be employed.

Phenylethylene oxide can for specific applications and/or in order to incorporate one or more phenolic rings into the molecule be combined with an ethylene oxide, propylene oxide and/or a butylene oxide. Such a combination can for example suitably be performed by either an intermediate reaction step following the addition step, during which step ethylene oxide, propylene oxide and/or butylene oxide are reacted with the alcohol, and prior to the acrylation step or through an initial reaction step prior to said addition of ethylene oxide, propylene oxide and/or butylene oxide, in which initial step phenylethylene oxide is added to the alcohol. In both cases is phenylethylene oxide added in an amount corresponding to the desired final properties.

The following process is a suitable process for ethoxylation, propoxylation, butoxylation and/or phenylethoxylation of 1,3-dioxane alcohols. The alcohol is charged in a reaction vessel equipped with a stirrer, temperature control and inlet of inert gas. An alkaline compound, such as potassium hydroxide, is thereafter charged as catalyst. The reaction mixture is heated to 100-160°C and a pressure of 2000-4000 mm Hg is applied. Ethylene oxide, propylene oxide, butylene oxide

and/or phenylethylene oxide (styrene oxide) is then, in an amount resulting in the desired degree of addition, slowly pumped into the reaction vessel. Suitable charging time is about 1 hour followed by a post-reaction during 30 minutes. The obtained product is usually neutralised to pH 6-8 by addition of for instance sodium hydrogenphosphate together with a small amount of water and a filter aid. The water is, after stirring for 1 hour at 100-150°C, evaporated by vacuum distillation. The product is finally filtered at 100°C and preferably stabilised by addition of an antioxidant such as butylhydroxytoluene (BHT).

Instead of above described addition, ethylene oxide, propylene oxide, butylene oxide and/or phenylethylene oxide can be replaced by equivalent glycols and/or polyglycols, whereby a conventional etherification is performed.

A suitable process for preparation of an acrylic and/or methacrylic ester of an ethoxylated, a propoxylated, a butoxylated and/or a phenylethoxylated 1,3-dioxane alcohol can be disclosed as follows. The alcohol compound, the acrylic or methacrylic acid and an azeotropic solvent, such as toluene, are charged into a reaction vessel provided with a stirrer, temperature control, air inlet and a cooler connected to a water-trap. Acrylic or methacrylic acid is charged in excess in relation to desired degree of acrylation and the amount of azeotropic solvent is suitably equal to the subtotal weight of charged raw materials. The reaction mixture is stirred until a clear solution is obtained, a heating to 40-60°C may be necessary. Inhibitors such as 2-methyl hydroquinone and nitrobenzene and a catalyst such as sulphonic acid are added and the reaction mixture is heated to reflux using an air sparge. The reflux is maintained until the desired degree of esterification is obtained and formed esterification water is continuously removed azeotropically. When the desired degree of acrylation



is obtained, the reaction mixture is cooled to room temperature and neutralised, usually to pH 7-8, with for instance an aqueous solution of sodium hydroxide. The water/salt phase is removed and the product/toluene phase is then repeatedly washed with water. The water phase is after each washing removed. Active carbon and a filter aid are following the washing added to the product/toluene phase, which phase thereafter is filtered. An antioxidant such as 2-methyl hydroquinone, is added to the product/toluene phase and residual toluene is evaporated under vacuum maintaining an air sparge. Acrylation can as alternative to a direct esterification as above, involve a transesterification.

Above described processes are suitable for 1,3-dioxane alcohols and ethoxylated, propoxylated, butoxylated and/or phenylethoxylated 1,3-dioxane alcohols, respectively, but other known processes can of course also be used.

The according to the invention obtained cycloaliphatic acrylic monomer exhibits excellent dilution properties as well as a low skin irritation, a high degree of through hardening, good final hardness, flexibility and resistance.

The cycloaliphatic acrylic monomer according to the invention can favourably be used as a component in radiation curing compositions. The percentage monomer is in such compositions within the range of 0.1-80% by weight, preferably 5-40% by weight. The radiation curing composition can for example be a printing ink, a paint, a lacquer, an adhesive, a dental material or the like. It is, besides radiation curing systems, also possible to use the monomer for the preparation of latex dispersions.

Radiation curing compositions most often comprise one or more oligomers in an amount of 10-80% by weight. Some commonly used

oligomers are for instance polyurethane acrylates, polyester acrylates, epoxy acrylates, silicone acrylates and unsaturated polyesters. Radiation curing compositions can furthermore comprise one or more, to the cycloaliphatic monomer according to the invention, additional mono, di and/or multifunctional acrylic monomers in amounts of 0.1-70% by weight. One or more initiators, for example photoinitiators such as benzophenones and aromatic keto compounds prepared from benzophenones such as alkylated and halogen-alkylated benzophenones are also present. Other suitable photoinitiators are for example anthraquinones, benzoines and derivatives thereof, acetophenones, acyloxime esters and benzil ketals. The percentage initiator in a radiation curing composition is normally 0.1-10% by weight. Above described compositions can be cured either by means of ultra-violet light or by means of electron-beams (so called UV and EB curing). Curing can also be performed by means of peroxides or other radical forming initiators.

The present invention is further explained in connection to enclosed embodiment examples 1-10 and enclosed figure 1, which disclose as follows:

- Examples 1 and 2: Ethoxylation of 1,3-dioxane alcohols.
- Examples 3 and 4: Acrylation of products according to Examples 1 and 2.
- Example 5: Skin irritating properties of the acrylic monomer according to Example 3.
- Examples 6 and 7: Preparation of an UV-curing lacquers based on products according to Examples 3 and 4.
- Examples 8-11: Evaluations of the UV-curing lacquers according to Example 6 and 7.

- Figure 1: Structural formulas for some selected compounds used as raw materials according to embodiments of the present invention.

The invention is not limited to disclosed embodiments as these can be modified variously within the scope of the invention.

#### Example 1

146 g (1 mole) of 5-ethyl-1,3-dioxane-5-methanol and 3.9 g of powdered potassium hydroxide were weighed into a 1 litre laboratory autoclave. The mixture was heated under stirring and nitrogen purge to 120°C. 132 g (3 moles) of ethylene oxide were during one hour, at a temperature of 120°C and a pressure of 2000-4000 mm Hg, pumped into the autoclave. A post-reaction was performed during 30 minutes at 120°C. A vacuum of < 1 mm Hg was thereafter applied, whereby possibly unreacted ethylene oxide and during the reaction formed low molecular glycols were evaporated. The obtained product was neutralised to pH 6-8 with 3% of sodium hydrogenphosphate together with 1.5% of water and 1.5% of a filter aid (Celite), calculated on charged raw materials. The water was after one hour of stirring at 120°C during 30 minutes evaporated at this temperature and a vacuum of < 1 mm Hg. Finally, the product was filtered at 100°C.

The obtained product consisted of 5-ethyl-1,3-dioxane-5-methanol-triethoxylate having the following characteristics:

Appearance:	Clear colourless liquid
Viscosity:	83 mPas at 23°C
Hydroxyl value:	201 mg KOH/g
pH (4% aqueous solution):	5.7

**Example 2**

Example 1 was repeated with the difference that 148 g (1 mole) of 1,3-dioxane-5,5-dimethanol was charged instead of 146 g (1 mole) of 5-ethyl-1,3-dioxane-5-methanol.

The obtained product consisted of 1,3-dioxane-5,5-dimethanol-triethoxylate having the following characteristics:

Appearance:	Clear colourless liquid
Viscosity:	520 mPas at 23°C
Hydroxyl value:	398 mg KOH/g
pH (4% aqueous solution):	6.8

**Example 3**

278 g (1 mole) of the product according to Example 1, 108 g (1.5 mole) of acrylic acid and 400 ml of toluene were charged in a glass flask equipped with a stirrer, air inlet, cooler and water-trap (Dean-Stark). 1600 ppm of 2-methyl hydroquinone and 200 ppm of nitrobenzene as inhibitors and 1.2% of methanesulphonic acid as catalyst were added. The charged components were mixed by stirring until a clear solution was obtained. The reaction mixture was thereafter heated to 120°C under air sparge. Water formed during the esterification was removed azeotropically. The reflux was maintained until the desired degree of esterification was obtained. The mixture was after 4.5 hours cooled to room temperature and neutralised with a 5% aqueous solution of sodium hydroxide. The water/salt phase was removed and the product/toluene phase was washed three times with water, which after each washing was removed. 5% of active carbon (0.6-1.5 mm Hydriffin BK) and 2% of a filter aid (Celite) was following the washings added to the product/toluene phase, which thereafter was heated to 90°C.

The product/toluene phase was kept at this temperature for 15 minutes, after which time it was cooled to room temperature and filtered. Following the filtration 200 ppm of 2-methyl hydroquinone was added and a vacuum of 20 mm Hg was applied. The residual toluene was evaporated at 20 mm Hg and a temperature of max. 40°C whilst maintaining an air sparge.

The obtained product consisted of 5-ethyl-1,3-dioxane-5-methanol-triethoxylate monoacrylate having the following characteristics:

Viscosity: 60 mPas at 23°C  
Colour according to Gardner: 3-4

#### Example 4

280 g (1 mole) of the product according to Example 2, 216 g (3 moles) of acrylic acid and 700 ml of toluene were charged in a glass flask equipped with a stirrer, air inlet, cooler and water-trap (Dean-Stark). 1600 ppm of 2-methyl hydroquinone and 200 ppm of nitrobenzene as inhibitors and 1.2% of methanesulphonic acid as catalyst were added. The charged components were mixed by stirring until a clear solution was obtained. The reaction mixture was thereafter heated to 130°C under air sparge. Water formed during the esterification was removed azeotropically. The reflux was maintained until the desired degree of esterification was obtained. The mixture was after 5 hours cooled to room temperature and neutralised with a 5% aqueous solution of sodium hydroxide. The water/salt phase was removed and the product/toluene phase was washed three times with water, which after each washing was removed. 5% of active carbon (0.6-1.5 mm Hydriffin BK) and 2% of a filter aid (Celite) was following the washings added to the product/toluene phase, which thereafter was heated to 70°C.

The product/toluene phase was kept at this temperature for 15 minutes, after which time it was cooled to room temperature and filtered. Following the filtration 200 ppm of 2-methyl hydroquinone was added and a vacuum of 20 mm Hg was applied. The residual toluene was evaporated at 20 mm Hg and a temperature of max. 40°C whilst maintaining an air sparge.

The obtained product consisted of 1,3-dioxane-5,5-dimethanol-triethoxylate diacrylate having the following characteristics:

Viscosity: 140 mPas at 23°C  
Colour according to Gardner: 7

#### Example 5

Skin irritation was determined for 5-ethyl-1,3-dioxane-5-methanol-triethoxylate monoacrylate obtained according to Example 2.

The evaluation was carried out in accordance with OECD Guideline for Testing of Chemicals no. 404, "Acute Dermal Irritation/Corrosion", of 12 May 1983.

The determination was performed by Scantox A/S, Lille Skensved, Denmark with the following results:

Erythema: 0.4  
Oedema: 1.1

According to Directive of the Commission 83/467/EEC, 29 July 1983, published in "Official Journal of the European Communities", L 257, 1983, is 5-ethyl-1,3-dioxane-5-methanol-triethoxylate monoacrylate not to be classified as skin irritating.

**Example 6**

A UV curing lacquer containing the product obtained according to Example 3 was prepared by mixing of below components.

25 parts of acrylic monomer according to Example 3  
50 parts of polyester oligomer (Laromer LR 8799, BASF AG, Germany)  
25 parts of trimethylolpropane triethoxylate triacrylate  
4 parts of UV-initiator (Darocure 1173, Firma E. Merck, Germany)

Obtained lacquer exhibited a viscosity of 335 mPas at 23°C.

**Example 7**

A UV curing lacquer containing the product obtained according to Example 4 was prepared by mixing of below components.

25 parts of acrylic monomer according to Example 4  
50 parts of polyester oligomer (Laromer LR 8799, BASF AG, Germany)  
25 parts of tripropylene glycol diacrylate  
4 parts of UV-initiator (Darocure 1173, Firma E. Merck, Germany)

Obtained lacquer exhibited a viscosity of 286 mPas at 23°C.

**Example 8**

The lacquers obtained according to Examples 6 and 7 were cured by means of a UV-lamp of 80W/cm and at a belt speed of 20 m/min. The lacquers were coated on glass panels at a

filmthickness of  $30 \pm 5 \mu\text{m}$  (cured) and were allowed to pass the UV-lamp 1, 2, 4, 8 and 16 times. The samples were after curing tempered for 24 hours at  $23 \pm 2^\circ\text{C}$  and  $50 \pm 5\%$  relative humidity, whereupon the filmhardness was measured by means of a König pendulum and according to Swedish Standard SS 184186 Edition 4.

The following results were obtained:

Number of passages	Pendulum hardness, König seconds	
	Lacquer according to	
	Example 6	Example 7
1	35	48
2	37	57
4	43	71
8	52	94
16	60	115

#### Example 9

The lacquers obtained according to Examples 6 and 7 were coated and cured as in Example 8.

The resistance after 16 passages under the UV-lamp was evaluated according to Swedish Standard SS 839118 Edition 2, which fully complies with ISO 4211-1979.

The evaluation scale according to above Standard is 0-5, wherein 5 is best.

The following results were obtained:



### Evaluation

Lacquer according to

	Example 6	Example 7
--	-----------	-----------

---

Acetone, 2 minutes	5	5
Ethanol 48%, 16 hours	5	5
Water, 24 hours	5	5

### Example 10

The lacquers obtained according to Examples 6 and 7 were coated on steel panels complying with ISO 1514 at a film-thickness of  $30 \pm 5 \mu\text{m}$  (cured) and cured as in Example 8. The scratch resistance as pencil hardness was determined according to ASTM 3363-74 (1989) and the flexibility was determined according to Swedish Standard SS 184177 Edition 3. Both determinations were carried out after 8 passages under the UV-lamp.

The following results were obtained:

	Lacquer according to	
	Example 6	Example 7
Scratch resistance	H-2H	HB-F
Flexibility	5.2 mm	5.3 mm

### Example 11

The lacquers obtained according to Examples 6 and 7 were coated and cured as in Example 8.

The degree of hardening through was determined by means of

IR-spectra and as unreacted unsaturation after 1 and 4 passages under the UV-lamp.

The degree of unsaturation in the lacquer prior to curing was normalised to 100.


The degree of hardening through is expressed as 100 minus unreacted unsaturation after curing.

The following results were obtained:

	Lacquer according to	
	Example 6	Example 7
Degree of hardening through after 1 passage	87%	80%
Degree of hardening through after 4 passages	92%	83%

## CLAIMS

1. Cycloaliphatic acrylic monomer characterised in, the general formula



in which formula

$R_1$  is H,  $CH_3$ , HO,  $HO-(R_3)_n$  or  $O-(R_3)_n-\overset{\overset{O}{\parallel}}{C}-CH_2$  and

$R_2$  is  $O-(R_3)_n-\overset{\overset{O}{\parallel}}{C}-CH_2$  wherein





$R_3$  is  $C_2H_4O$ ,  $C_3H_6O$ ,  $C_4H_8O$ ,  $C_8H_8O$  or combinations thereof,

$R_4$  is H or  $CH_3$  and wherein the mean value  $\bar{n}$  for  $n$  is 1-24.


2. Acrylic monomer according to claim 1 characterised in, that  $R_3$  is  $C_2H_4O$  and the mean value  $\bar{n}$  for  $n$  is 2-8.

3. Acrylic monomer according to claim 1 characterised in, that  $R_3$  is  $C_3H_6O$  and the mean value  $\bar{n}$  for  $n$  is 2-6.


4. Acrylic monomer according to claim 1 characterised in, that the mean value  $\bar{n}$  for  $n$  is 2-8 and that  $(R_3)_n$  is  $(C_3H_6O)_m(C_2H_4O)_n$  wherein the mean value  $\bar{m}$  for  $m$  is 1.
5. Use of an acrylic monomer according to any of the claims 1-4 in a radiation curing composition characterised in, that the acrylic monomer constitutes 0.1-80% by weight, preferably 5-40% by weight, of the composition.
6. Use according to claim 5 characterised in, that the radiation curing composition consists of a paint, a lacquer, a printing ink, an adhesive or a dental material.

**FIG. 1**5-Methyl-1,3-dioxane-  
-5-methanol5-Ethyl-1,3-dioxane-  
-5-methanol1,3-dioxane-  
-5,5-dimethanol


Ethylene oxide






Propylene oxide



1,2-Butylene oxide



2,3-Butylene oxide

Phenylethylene oxide  
(Styrene oxide)

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00360

<b>A. CLASSIFICATION OF SUBJECT MATTER</b>		
IPC5: C07D 319/06, C08F 120/18, C08G 65/32, C08G 63/19 According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b>		
Minimum documentation searched (classification system followed by classification symbols)		
IPC5: C07D, C08F, C08G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
CAS-ONLINE		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 3267084 (GULF OIL CORPORATION), 16 August 1966 (16.08.66) --	1-6
A	EP, A2, 0397492 (HOECHST CELANESE CORPORATION), 14 November 1990 (14.11.90) --	1-6
A	EP, A1, 0090174 (BAYER AG), 5 October 1983 (05.10.83), see the examples --	1-6
A	EP, A1, 0347381 (CIBA-GEIGY AG), 20 December 1989 (20.12.89), see example 2 --	1-6
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
16 August 1993		24 -08- 1993
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86		Authorized officer Göran Karlsson Telephone No. +46 8 782 25 00

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00360

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	Patent Abstracts of Japan, Vol 12, No 344, C-528, abstract of JP, A, 63-101377 (KYOWA GAS CHEM IND CO LTD et al), 6 May 1988 (06.05.88)  -- -----	1-6

# INTERNATIONAL SEARCH REPORT

Information on patent family members

02/07/93

International application No.

PCT/SE 93/00360

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 3267084	16/08/66	FR-A- 1365415	00/00/00
EP-A2- 0397492	14/11/90	CA-A- 2015848	12/11/90
		CN-A- 1047509	05/12/90
		JP-A- 3021619	30/01/91
		US-A- 5004798	02/04/91
EP-A1- 0090174	05/10/83	DE-A- 3208438	15/09/83
EP-A1- 0347381	20/12/89	SE-T3- 0347381	
		JP-A- 2051509	21/02/90
		US-A- 5059698	22/10/91